




































POPLAR



POPLAR CO., LTD.


















松江實業股份有限公司



Glaze Stain 20 Series

Product No.	Color	System	Max. Temp.	Atmosphere	Transparent Glaze	Opaque Glaze
20101	Chromium Green	Al-Cr	1300 ⁰ C	Oxidation~ Reduction		
20102	Peacock Green	Al-Cr-Co	1300 ⁰ C	Oxidation~ Reduction		
20104	Chromium Green	Al-Cr	1300 ⁰ C	Oxidation~ Reduction		
20106	Peacock Green	Al-Cr-Co	1300 ⁰ C	Oxidation~ Reduction		
20111	Moss Green	Zr-Pr-V	1250 ⁰ C	Oxidation		
20202	Turquoise Blue	Zr-Si-V	1280 ⁰ C	Oxidation~ Reduction		
20203	Turquoise Blue	Zr-Si-V	1280 ⁰ C	Oxidation~ Reduction		
20234	Cobalt Blue	Al-Si-Co	1300 ⁰ C	Oxidation~ Reduction		
20235	Royal Bule	Si-Co	1300 ⁰ C	Oxidation~ Reduction		
20236	Cobalt Blue	Al-Si-Co	1300 ⁰ C	Oxidation~ Reduction		
20266	Cobalt Blue	Al-Co-Cr	1300 ⁰ C	Oxidation~ Reduction		
20281	Peacock Blue	Al-Co-Cr	1300 ⁰ C	Oxidation~ Reduction		
20301	Pr Yellow	Zr-Si-Pr	1250 ⁰ C	Oxidation		
20303	Pr Yellow	Zr-Si-Pr	1250 ⁰ C	Oxidation		
20313	Vanadium Yellow	Zr.-V	1250 ⁰ C	Oxidation		
20315	Vanadium Yellow	Zr-V	1350 ⁰ C	Oxidation~ Reduction		

Product No.	Color	System	Max. Temp.	Atmosphere	Transparent Glaze	Opaque Glaze
20323	Titanium Yellow	Ti-Sb-Cr	1250 ⁰ C	Oxidation		
20333	Titanium Yellow	Ti-Sb-Cr	1250 ⁰ C	Oxidation		
20404	Black	Co-Fe-Cr	1280 ⁰	Oxidation		
20405	Black	Co-Fe-Cr	1280 ⁰	Oxidation~Reduction		
20406	Black	Co-Fe-Cr	1280 ⁰	Oxidation		
20505	Blue Grey	Zr-Co-Si	1250 ⁰	Oxidation		
20506	Brown Grey	Zr-Co-Ni-Si	1280 ⁰	Oxidation		
20507	Grey	Zr-Co-Si	1280 ⁰	Oxidation~Reduction		
20606	Brown	Al-Zn-Cr-Fe	1280 ⁰	Oxidation		
20617	Brown	Al-Zn-Cr-Fe	1250 ⁰	Oxidation		
20620	Red Brown	Al-Zn-Cr-Fe	1200 ⁰	Oxidation		
20630	Coffee Brown	Al-Zn-Cr-Fe	1200 ⁰	Oxidation		
20650	Dark Brown	Al-Zn-Cr-Fe	1200 ⁰	Oxidation		
20696	Brown	Al-Zn-Cr-Fe	1250 ⁰	Oxidation		
20705	Dark Coral Pink	Zr-Si-Fe	1250 ⁰	Oxidation		
20706	Iron Red	Zr-Si-Fe	1250 ⁰	Oxidation		
20727	Pink	Sn-Cr-Ca	1250 ⁰	Oxidation		

Product No.	Color	System	Max. Temp.	Atmosphere	Transparent Glaze	Opaque Glaze
20735	Alumina Pink	Al-Zn-Cr-Fe	1250 ⁰	Oxidation		
20745	Maroon	Sn-Cr-Ca	1250 ⁰	Oxidation		
20746	Dark Maroon	Sn-Cr-Ca	1250 ⁰	Oxidation		
20747	Maroon	Sn-Cr-Ca	1250 ⁰	Oxidation		
20749	Dark Maroon	Sn-Cr-Ca	1250 ⁰	Oxidation		
20757	Rose Maroon	Sn-Cr-Ca	1250 ⁰	Oxidation		
20790	Dark Red	Zr-Si-Cd-Se	1250 ⁰	Oxidation		
20794	Cd Yellow	Zr-Si-Cd-Se	1250 ⁰	Oxidation		
20797	Dark Red	Zr-Si-Cd-Se	1250 ⁰	Oxidation		
20808	Violet	Sn-Cr	1250 ⁰	Oxidation		

A decorative graphic consisting of several colored circles in shades of yellow, orange, and red, arranged in a cluster to the right of the "Contact Us" button.A large, orange, rounded rectangular button with the text "Contact Us" in a dark blue, serif font.

Contact Us

A vertical rectangular image with a textured, abstract appearance in shades of brown, orange, and yellow, resembling a close-up of a tree trunk or bark.

Head Office

No. 33, Lane 12, Chi Lin Road, Taipei, Taiwan

Tel: +886-2-2561-8191

Fax: +886-2-2541-8008

Email: poplarsg@ms58.hinet.net

Http:// www.poplar.com.tw